

# AQUATOP

## Construction:

Substrate: Two-ply 100% Polyester Plain Weave  
Coating: Durable, Lightfast Pigmented Polymeric Resins

## Typical Properties:

## Federal Test Method 191-A

Width (in.)	60"	FTM-5020
Weight (oz./yd)	9.25 oz.	FTM-5041
Grab-Tensile (lbs.)		
Warp	450	FTM-5100
Fill	350	
Tongue-Tears (lbs.)		
Warp	22	FTM-5134
Fill	20	
Crock		
Dry	4	FTM-5651
Wet	4	
Hydrostat-Height (cm)	90+	FTM-5514
Hydrostat-Leakage (8-10 min)	0	FTM-5516
Spray Rating	100	FTM-5526
Stretch W & F	1-2%	
Bag Test, 8 hrs	Pass	

**SOLD BY THE YARD OR SAVE BIG MONEY AND BUY A ROLL!**

## Rochford Supply

1500 Washington Ave N, Minneapolis, MN 55411

1-800-334-6414 • 612-588-9000 • F: 612-588-3000

[info@rochfordsupply.com](mailto:info@rochfordsupply.com)

**ORDER ONLINE!**

[www.rochfordsupply.com](http://www.rochfordsupply.com)