


SOFTOUCH BY ODYSSEY

Technical Data

SOFTOUCH BY ODYSSEY is a combination of an acrylic coated woven polyester and a soft non-woven backer of 100% polyester. With the development of SOFTOUCH BY ODYSSEY, fabricating professionals can now provide their customers with a material that has the strength, dimensional stability and water and abrasion resistance they expect from ODYSSEY III along with a scratch resistant softness that comes from the non-woven backer. Now fabricators, covering sensitive gelcoats, critical printed surfaces and delicate objects, can provide worry-free protection using SOFTOUCH BY ODYSSEY.

Width	60"
Weight FED-STD-191 Method 5041	11.00 oz./yd ²
Tensile ASTM-D1682-7.01	Warp = 325 pounds Fill = 263 pounds
Tongue Tear ASTM-D2261-7.01	Warp = 30 pounds Fill = 46 pounds
Trapezoidal Tear ASTM-D4533-4.08	Warp = 55 pounds Fill = 56 pounds
Elmendorf Tear ASTM-D424-7.01	Warp = 14+ Fill = 14+
Hydrostatic Resistance 8" for 10 minutes FED-STD-191 Method 5516	0 millimeters



Rochford Supply, Inc.

1500 Washington Avenue North
Minneapolis, Minnesota 55411

(612) 588-9000 Fax (612) 588-3000

E-Mail: rochfordsupply@rochfordsupply.com

www.rochfordsupply.com